

# Accura® 25

Flexible plastic to simulate and replace CNC machined white polypropylene articles



## Technical Data


Post-Cured Material			
Measurement	Condition	Metric	U.S.
Tensile Strength (MPa/PSI)	ASTM D 638	55-58	5540-5570
Tensile Modulus (MPa/KSI)	ASTM D 638	1590-1660	230-240
Elongation at Break (%)	ASTM D 638	13-20	13-20
Flexural Strength (MPa/PSI)	ASTM D 790	55-58	7960-8410
Flexural Modulus(MPa/KSI)	ASTM D 790	1380-1660	200-240
Impact Strength (J/m /Ft-lbs/in)	ASTM D 256	19-24	0.4
Heat Deflection Temperature (°C/°F)	ASTM D 648 @ 66 PSI	58-63	136-145
	@ 264 PSI	51-55	124-131
Coefficient of Thermal Expansion ( $\mu$ mm/m °C / $\mu$ in/in °F)	ASTM E 831-93 TMA (T<T <sub>g</sub> , 0-20 °C)	$107 \times 10^{-6}$	59.4
	TMA (T<T <sub>g</sub> , 75-140 °C)	$151 \times 10^{-6}$	83.9
Glass Transition - T <sub>g</sub> (°C/°F)	DMA, E''	72-74	162-165
Shore D		80	80

### Liquid Material

Measurement	Condition	Value
Viscosity	@ 30 °C (86 °F)	250 cps
Penetration Depth (Dp)		4.2 mils
Critical Exposure (Ec)		10.5 mJ/cm <sup>2</sup>
Color		White
Solid Density	@ 25 °C (77 °F)	1.19 g/cm <sup>3</sup> at 25 °C
Liquid Density	@ 25 °C (77 °F)	1.13 g/cm <sup>3</sup> at 25 °C

## Features

- Flexible
- Snap fit assemblies
- Master patterns for vacuum casting
- Durable functional prototypes



**3DSYSTEMS®**

**UK**  
Tel: +44 1442 282 600  
[info@3dsystems-europe.com](mailto:info@3dsystems-europe.com)

**Germany, Scandinavia,  
Eastern Europe, Middle East**  
Tel: +49 6151 357 0  
[info@3dsystems-europe.com](mailto:info@3dsystems-europe.com)

**USA**  
Tel: +1 803.326.3900  
[moreinfo@3dsystems.com](mailto:moreinfo@3dsystems.com)

**Asia-Pacific**  
Melbourne Tel: +61 3 9819 4422  
Sydney Tel: +61 2 9516 5571  
[3dprinters.asiapac@3dsystems.com](mailto:3dprinters.asiapac@3dsystems.com)

**MANUFACTURING THE FUTURE™**

Warranty/Disclaimer: The performance characteristics of these products may vary according to product application, operating conditions, or with end use. 3D Systems makes no warranties of any type, express or implied, including, but not limited to, the warranties of merchantability or fitness for a particular use.

© 2015 by 3D Systems, Inc. All rights reserved. Specifications subject to change without notice. The 3D logo and Accura are registered trademarks of 3D Systems, Inc.